



Den Braven

BETTER RESULTS
THROUGH KNOWLEDGE

REFERENCE SERIES



Silicone Colours

Coloured neutral silicone for sanitary, glazing and façade joints

- Wide variety of standard colours
- Universal contractors silicone
- 100% neutral silicone
- For façade, glazing and sanitary
- Very good adhesion
- Almost odourless

AVAILABLE IN A WIDE VARIETY
OF COLOURS

Silicone Colours

Coloured neutral silicone for sanitary, glazing and façade joints

- Wide variety of standard colours
- Universal contractors silicone
- 100% neutral silicone
- For façade, glazing and sanitary
- Very good adhesion
- Almost odourless

Applications

Den Braven SILICONE COLOURS is specially developed for durable elastic sealing of expansion joints in concrete and brickwork, connections joints, curtain wall, glazing systems, constructions, kitchens, bathrooms, showers and industrial applications.

Directions of Use

A well-designed joint is a joint with a sufficient width so it would be able to take and process the movement of the adjacent building elements. The joint depth should always be in the correct relationship of the joint width. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10 mm is 1:1, with a minimum of 5 mm in width and depth. For joints wider than 10 mm, the ratio is 1:2 with a minimum depth of at least 10 mm and a maximum of 15 mm. For further information please contact our technical service.

Packaging

Cartridges 310 ml, 12 per box
Sausages 600 ml, 12 per box

Colours

RAL 1002, RAL 1013, RAL 1015, RAL 3004, RAL 3005, RAL 3007, RAL 3020, RAL 5010, RAL 5011, RAL 6005, RAL 6009, RAL 6022, RAL 7006, RAL 7011, RAL 7012, RAL 7015, RAL 7016, RAL 7021, RAL 7022, RAL 7030, RAL 7032, RAL 7035, RAL 7039, RAL 7042, RAL 7047, RAL 8003, RAL 8007, RAL 8014, RAL 8017, RAL 9001, RAL 9003, RAL 9007, RAL 9010, transparent grey.

Shelf Life


Shelf life of 12 months after production date in unopened original packaging between +5°C and +25°C stored in a dry place.

Certifications

- EN 15651-1: F-EXT-INT-CC 25LM
- EN 15651-2: G-CC 25LM
- EN 15651-3: S XS1

Additional information:

Base	Neutral Alcoxy
Density	1.02 g/ml
Shore A	12
Joint Movement	25%
Tensile Strength	1.00 MPa
100% Modulus	0.25 MPa
Elongation @ Break	500%
Curing Time	5 mm / day
Skin Formation	12 min.
Application Temp.	+5°C to +40°C
Temp. Resistance	-40°C to +120°C



Den Braven,
P.O. Box 194, 4900 AD Oosterhout, The Netherlands
Tel. +31 (0)162-491000, www.denbraven.com